

Jotafloor Sealer

Product description

This is a two component amide cured epoxy coating. It is transparent. It exhibits excellent penetration properties to ensure good adhesion on most concrete floors in atmospheric environments only. Especially suited for properly prepared concrete substrates.

Scope

The Application Guide offers product details and recommended practices for the use of the product.

The data and information provided are not definite requirements. They are guidelines to assist with efficient and safe use, and optimum service of the product. Adherence to the guidelines does not relieve the applicator of responsibility for ensuring that the work meets specification requirements. Jotuns liability is in accordance with general product liability rules.

The Application Guide (AG) must be read in conjunction with the relevant specification, Technical Data Sheet (TDS) and Safety Data Sheet (SDS) for all the products used as part of the coating system.

Referred standards

Reference is generally made to ASTM and SSPC Standards. When using standards from other regions it is recommended to reference only one corresponding standard for the substrate being treated.

Application

Acceptable environmental conditions - before and during application

All cementitious substrate should be 28 days old and before the application, test the atmospheric conditions in the vicinity of the substrate for the dew formation according to ISO 8502-4.

The moisture content should not exceed 5%.

The Relative Humidity should not exceed 80%.

Minimum and maximum temperature should be 23°C and 40°C respectively.

Substrate temperature should be at least 3°C above the dew point.

The PH of the concrete should be 7-9.

The following restrictions must be observed:

- Only apply the coating when the substrate temperature is at least 3°C above the dew point
- Do not apply the coating if the substrate is wet or likely to become wet
- Do not apply the coating if the weather is clearly deteriorating or unfavorable for application or curing
- Do not apply the coating in high wind conditions

Surface preparation

The required quality of surface preparation can vary depending on the area of use, expected durability and if applicable, project specification.

Preferred surface profile for Jotafloor Sealer is CSP2-CSP5 as per the ICRI guideline mentioned in 310.2R.2013.

The substrate should be mechanically abraded to leave a clean, sound, stable base on to which Jotafloor system can be applied. Preferred method of abrading the substrate is diamond disc grinding or dust free captive blasting. Both the equipment should be connected to an industrial vacuum machine for a dust free environment.

Whichever surface preparation method is employed, ensure that the laitance (powdery material on the concrete surface) and loose particles are removed from the concrete surface. After the surface preparation is completed, remove all the dust formed on the surface an industrial vacuum machine.

Once surface preparation is completed it is necessary to use the following material for concrete repairs Jotafloor Filler – Blow holes/Cracks up to 3 mm depth Jotafloor Filler Plus – Blow holes / cracks from 3 mm to 10 mm depth Slurry of Jotafloor SF PR 150 and Non -slip aggregate medium – Blow holes/cracks more than 10 mm depth.

For every 1 liter of Jotafloor SF PR 150 it is required to add 5 kgs of non - slip aggregate medium and then mix. The mixed quantity would be in solid form and should be applied on to the wet primer for adhesion. It is important to consult the Jotun Technical team for any repair above 10 mm deep.

Coating should not be relied upon to improve the tolerance's or flatness levels in the substrate. The substrate should be prepared to the appropriate tolerance prior to the application of coating. Tolerance's can be corrected, moreover this is a separate operation which must be completed before installing the coating. Coating will generally follow the contours of the substrate and have the same tolerance's as the substrate to which it is applied. Applicators are advised to check the tolerances of the substrate before they begin with the preparation.

Product mixing

Product mixing ratio (by volume)

Jotafloor Sealer Comp A	4 part(s)
Jotafloor Sealer Comp B	1 part(s)

The temperature of base and curing agent is recommended to be 18 °C or higher when the paint is mixed.

Induction time and Pot life

Paint temperature	23 °C
Pot life	20 min

Jotafloor Sealer is a two-component product supplied with the base (Component A) and the hardener (Component B). Add the entire contents of the Comp B to the base Comp A and mechanically mix for the two components for 2 minutes.

Thinner/Cleaning solvent

Cleaning solvent: Jotun Thinner No. 17

No dilution is required.

Application data

Apply Jotafloor Sealer using a roller at 8 sqm/liter to achieve a desired thickness of 130 microns WFT. The mentioned coverage is theoretical and the practical coverage on site will depend upon the concrete surface profile.

Repair of coating system

Damages to the coating layers:

Prepare the area through sandpapering or grinding, followed by thorough cleaning/vacuuming. When the surface is clean and dry the coating may be over coated by itself or by another product, ref. original specification.

Always observe the maximum over coating intervals. If the maximum over coating interval is exceeded the surface should be carefully roughened in order to ensure good intercoat adhesion. **Damages exposing bare substrate:**

Remove all rust, loose paint, grease or other contaminants by spot blasting, mechanical grinding, water and/or solvent washing. Feather edges and roughen the overlap zone of surrounding intact coating. Apply the coating system specified for repair.

Film thickness per coat

Typical recommended specification range

Dry film thickness	30 - 50	µm
Wet film thickness	80 - 130	µm
Theoretical spreading rate	13.3 - 8	m ² /l

Ventilation

Sufficient ventilation is very important to ensure proper drying/curing of the film.

Drying and Curing time

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	2 h	1 h	30 min
Walk-on-dry	14 h	6.5 h	3 h
Dry to over coat, minimum	8 h	4 h	1.5 h
Dried/cured for service	14 d	7 d	2 d

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dry to over coat, maximum, atmospheric: The longest time allowed before the next coat can be applied.

Temperature below 23 degree C will make application more difficult and careful considerations should be given to storage of materials in cold conditions. Consult Jotun technical team for assistance in such cases.

Maximum over coating intervals

Maximum time before thorough surface preparation is required. The surface must be clean and dry and suitable for over coating. Inspect the surface for chalking and other contamination and if present, remove with an alkaline detergent. Agitate the surface to activate the cleaner and before it dries, wash the treated area by low-pressure water cleaning using fresh water.

If maximum over coating interval is exceeded the surface should in addition be carefully roughened to ensure good inter coat adhesion.

Areas for atmospheric exposure

Average temperature during drying/curing	10 °C	23 °C	40 °C
Itself	5 d	3 d	2 d
epoxy	5 d	3 d	2 d
polyurethane	5 d	3 d	2 d

Equipment List

- Mixing paddle, MR3 type or equivalent
- Slow speed drill
- Paint rollers
- Cleaning cloth
- Medium-sized flat bladed screwdriver (for opening tins)
- Jotun Thinner 17 for cleaning
- Soft bristled sweeping brush or broom
- Heavy duty wire brush
- Diamond disc grinding machine
- Captive Blasting machine
- Industrial vacuum cleaner

Quality assurance

The following information is the minimum required. The specification may have additional requirements.

- Confirm that all welding and other metal work has been completed before commencing pre-treatment and surface preparation
- Confirm that installed ventilation is balanced and has the capacity to deliver and maintain the RAQ
- Confirm that the required surface preparation standard has been achieved and is held prior to coating application
- Confirm that the climatic conditions are within recommendations in the AG, and are held during the application
- Confirm that the required number of stripe coats have been applied
- Confirm that each coat meets the DFT requirements in the specification
- Confirm that the coating has not been adversely affected by rain or other factors during curing
- Observe that adequate coverage has been achieved on corners, crevices, edges and surfaces where the spray gun cannot be positioned so that its spray impinges on the surface at 90° angle
- Observe that the coating is free from defects, discontinuities, insects, abrasive media and other contamination
- Observe that the coating is free from misses, sags, runs, wrinkles, fat edges, mud cracking, blistering, obvious pinholes, excessive dry spray, heavy brush marks and excessive film build
- Observe that the uniformity and colour are satisfactory

All noted defects shall be fully repaired to conform to the coating specification.

Caution

This product is for professional use only. The applicator and operator shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators should use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

For further advice please contact your local Jotun office.

Health and safety

Please observe the precautionary notices displayed in the container. Use under well-ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and sought medical attention immediately.

Accuracy of information

Always refer to and use the current (last issued) version of the TDS, SDS and if available, the AG for this product. Always refer to and use the current (last issued) version of all International and Local Authority Standards referred to in the TDS, AG & SDS for this product.

Colour variation

Some coatings used as the final coat may fade and chalk in time when exposed to sunlight and weathering effects. Coatings designed for high temperature service can undergo colour changes without affecting performance. Some slight colour variation can occur from batch to batch. When long term colour and gloss retention is required, please seek advice from your local Jotun office for assistance in selection of the most suitable top coat for the exposure conditions and durability requirements.

Reference to related documents

The Application Guide (AG) must be read in conjunction with the relevant specification, Technical Data Sheet (TDS) and Safety Data Sheet (SDS) for all the products used as part of the coating system.

When applicable, refer to the separate application procedure for Jotun products that are approved to classification societies such as PSPC, IMO, SSPC etc.

Symbols and abbreviations

min = minutes	TDS = Technical Data Sheet
h = hours	AG = Application Guide
d = days	SDS = Safety Data Sheet
°C = degree Celsius	VOC = Volatile Organic Compound
° = unit of angle	MCI = Jotun Multi Colour Industry (tinted colour)
µm = microns = micrometres	RAQ = Required air quantity
g/l = grams per litre	PPE = Personal Protective Equipment
g/kg = grams per kilogram	EU = European Union
m ² /l = square metres per litre	UK = United Kingdom
mg/m ² = milligrams per square metre	EPA = Environmental Protection Agency
psi = unit of pressure, pounds/inch ²	ISO = International Standards Organisation
Bar = unit of pressure	ASTM = American Society of Testing and Materials
RH = Relative humidity (% RH)	AS/NZS = Australian/New Zealand Standards
UV = Ultraviolet	NACE = National Association of Corrosion Engineers
DFT = dry film thickness	SSPC = The Society for Protective Coatings
WFT = wet film thickness	PSPC = Performance Standard for Protective Coatings
	IMO = International Maritime Organization

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the data given without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.